

**Ag Alloys
(Sterling Silver)**

Part No	Nominal Compositions	
	%Ag	%Cu
HHAGCU999-50	50	50
HHAGCU999-92.5	92.5	7.5

**Au Alloys
(Yellow Gold)**

Part No	Kt	Nominal Compositions			
		%Au	%Cu	%Zn	%Ag
60010-1	10	41.7	40.3	10.0	8.0
60010-2	14	58.3	24.0	4.7	13.0
60010-3	18	75.0	16.0	3.0	6.0

**Au Alloys
(Ni) Yellow Gold)**

Part No	Kt	Nominal Compositions				
		%Au	%Cu	%Zn	%Ag	%Ni
60020-1	14	58.3	28.0	4.0	7.0	2.7
60020-2	18	75.0	10.0	2.0	11.0	2.0
60020-3	22	92.0	3.5	1.0	2.3	1.0

**Au Alloys
(White Gold)**

Part No	Kt	Nominal Compositions				
		%Au	%Cu	%Zn	%Ni	%Pd
60030-1	14	58.3	23.0	7.5	8.2	3.0
60030-2	18	75.0	14.0	3.0	6.0	2.0
60030-3	22	92.0	2.0	1.0	1.0	4.0